

Biresin® CR83 Composite resin system

Product Description

Biresin® CR83 is an epoxy resin system with extremely low viscosity designed specifically for the infusion process for the production of high performance fibre reinforced composites parts and moulds. The system has thermal properties up to 80°C. Biresin® CR83 epoxy resin has a low tendency to crystallise.

Application Areas

Biresin® CR83 is especially suited to the infusion and injection processes due to its low viscosity range. It can be used in the marine and general industrial composite areas. Due to its good wetting properties it is particularly suited for use with carbon fibre reinforcement.

Features / Advantages


- 3 hardeners (B) give a wide range of processing times
- The reactivity can be adapted by mixing the hardeners
- Fast infusion and good wet-out of fabrics and non-wovens due to low viscosity and good wetting characteristics even at low temperatures
- All systems Germanischer Lloyd approved, Certificate No. WP 1420017 HH (attached)
- Glass transition temperatures up to 80°C dependent on curing conditions
- Carbon fibres are wet out well by all of the resin systems
- Biresin® CR83 resin (A) has a low tendency to crystallise

Physical Data	Resin (A)	Hardener (B)		
Individual Components	Biresin® CR83	Biresin® CH83-2	Biresin® CH83-6	Biresin® CH83-10
Mixing ratio, parts by weight	100	30		
Mixing ratio, parts by volume	100	36		
Colour	translucent	colourless to yellowish		
Viscosity, 25°C mPa.s	~610	<10	<10	< 10
Density, 25°C g/ml	1.14	0.95	0.94	0.95
		Mixture		
Potlife, 100 g / RT, approx. values min		60	180	300
Mixed viscosity, 25°C, approx. values mPa.s		155	170	155


Processing

- The material and processing temperatures should be in the range 18 - 35°C.
- The mixing ratio must be followed accurately to obtain best results. Deviating from the correct mix ratio will lead to lower performance.
- The final mechanical and thermal values are dependent on the applied postcuring cycles.
- It is recommended to clean brushes or tools immediately after use with Sika Reinigungsmittel 5.
- Additional information is available in "Processing Instructions for Composite Resins".

Development of Exotherm of Biresin® CR83-Resin (A)-Hardener (B)-Mixtures, 100g / RT, insulated



Development of Viscosity of Biresin® CR83 (A)-Resin-Hardener (B)-Mixtures, 25°C




Typical Mechanical Properties of Fully Cured Neat Resin

Biresin® CR83 resin (A)	with hardener (B) Biresin®		CH83-2	CH83-6	CH83-10
Tensile strength	ISO 527	MPa	84	91	86
Tensile E-Modulus	ISO 527	MPa	2,960	3,200	3,100
Elongation at break	ISO 527	%	6.7	8.4	7.9
Flexural strength	ISO 178	MPa	129	134	131
Flexural E-Modulus	ISO 178	MPa	3,125	3,360	3,340
Compressive strength	ISO 604	N/mm ²	107	111	109
Density	ISO 1183	g/cm ³	1.15	1.15	1.15
Shore-hardness	ISO 868		D 85	D 85	D 85
Impact resistance	ISO 179	kJ/m ²	93	84	83

Typical Thermal Properties of Fully Cured Neat Resin

Biresin® CR83 resin (A)	with hardener (B) Biresin®		CH83-2	CH83-6	CH83-10
Heat distortion temperature	ISO 75B	°C	79	79	78
Glass transition temperature	ISO 11357	°C	84	80	81

Glass Transition Temperature vs. Cure Cycle



When curing a composite part, the whole of the part (including the very middle of the laminate) needs to see the cure temperature.

Packaging (net weight, kg)

Biresin® CR83 resin (A)	1,000	200	10
Biresin® CH83-2 hardener (B)		180	20
Biresin® CH83-6 hardener (B)		180	20
Biresin® CH83-10 hardener (B)		180	20

Storage

- Minimum shelf life of Biresin® CR83 resin (A) is 24 month and of Biresin® CH83-2, CH83-6 and CH83-10 hardeners (B) is 12 month under room conditions (18 - 25°C), when stored in original unopened containers.
- The tendency to crystallise with this system is very low. However, if crystallisation of the resin (A) component appears, it can be easily removed by warming up the resin for a sufficient time to at least 60°C.
- Containers must be closed tightly immediately after use. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

Sika Deutschland GmbH

Subsidiary Bad Urach

Stuttgarter Str. 139

D - 72574 Bad Urach

Germany

Tel: +49 (0) 7125 940 492

Fax: +49 (0) 7125 940 401

Email: tooling@de.sika.com

Internet: www.sika.com



Statement of Approval



Approval No. **WP 1420017 HH**

The material described below complies with the applicable requirements as given in the Rules and Regulations of Germanischer Lloyd. On this basis the material is

approved as **Laminating Resin**

for the construction of components provided that the recommendations for use as specified by the producer are observed.

Type	Biresin CR83
Description	Two Component Epoxy Resin System
Producer	SIKA Deutschland GmbH Stuttgarter Str. 139 72574 Bad Urach Germany
Normative Reference	Rules for Classification and Construction, II - Material and Welding Technology Part 2 Non-Metallic Materials

This document consists of this page and a one-page annex which is integral part of the approval.

This Statement of Approval is valid until 2018-03-18.

Hamburg, 2014-03-19

Germanischer Lloyd


Guido Michalek


Joachim Röhlein

Statement of Approval



ANNEX

Approval No. WP 1420017 HH

Date: 2014-03-19

Page 1 of 1

- Reference Documents Technical specifications deposited at Germanischer Lloyd Head Office.
- Assessed Documents
- Technical Data Sheet
 - Test Report issued by IFB Stuttgart, dated 2009-12-10.
- Fields of Application Construction of FRP laminates of components, on condition that the fibre reinforcements comply with the applicable requirements of the Germanischer Lloyd and are compatible to the resin.
- Approved Variants Epoxy Resin Biresin CR83 with following hardeners:
- Biresin CH83-2
 - Biresin CH83-6
 - Biresin CH83-10
- Limitations Any significant changes in design and/or quality of the material will render the approval invalid.
- Remarks This certificate supersedes the approval WP 1020014 HH.
- End of Annex

Germanischer Lloyd