

## ZC 20 BASE

RTV2 Silicone Rubber for industrial use.

Bicomponent poly-condensation silicone indicated for Mold making applications.

### 1. Main Characteristics

ZC 20 BASE is a poly-condensation curing, two component silicone that vulcanize at room temperature. It presents the following special features:

- Medium Shore A hardness (approx. 20)
- High tear strength
- Low dimensional variation

### 2. Applications

ZC 20 BASE is indicated for use in the following application:

- Industrial (low dimensional variation, high mechanical resistance, long life of the mold).

### 3. Processing

Before the casting of Epoxy, Polyester and PU resins on the silicone please apply a release agent to protect the silicone mould. If the resin is aggressive, apply it for each casting.

If you use for the first-time this silicone or a new resin, please do a small test before it does not compromise the work.

Take the two bi-component products supplied by Zhermack (BASE and ZC 120 NON FLAMMABLE CURING AGENT) and shake before use in order to homogenize each component prior to mixing. BASE component is white, ZC 120 NON FLAMMABLE CURING AGENT component is transparent/yellowish.

Mixing ratio must be 100:5 (5 units of ZC 120 NON FLAMMABLE CURING AGENT for every 100 basic units). For example, for 1 kg of base, add 50 g of hardener. This ratio must be respected to ensure the final characteristics of the product. DO NOT exceed the recommended ratio for the curing agent. You can use less ZC 120 NON FLAMMABLE CURING AGENT (3-4%) than the recommended ratio (5%), in this case the dimensional change will be lower but setting time will increase.

The hardness is reached after a few hours (see table) and if the correct percentage of catalyst is respected. After 24 hours the product is cured. After 72 hours, perfectly hardened.

Mix vigorously until the mixed white color is homogeneous. Once the product is completely mixed, it is ready to be melted and it is recommended to pour the silicone from a height of 30 cm into the mold.

Complete curing takes about 72 hours after mixing the two components. However, the product can be disassembled in just 18-24 hours.

The WT value in the table refers to a standard temperature of 23 °C. The ST setting time is the time required for the silicone to harden from the start of mixing the two components. The ST shown in the table refers to a standard temperature of 23 °C.

#### 4. Important recommendations

- Before handling the product, read the safety data sheet and make sure to get all the information required for safe use.
- Test the product in small scale quantity before extending the use in larger scale.
- Condensation bases accelerate naturally near the expiration date; it is recommended to use, in this case, less catalyst so that the product acquires flexibility and withdrawal.
- Before use, homogenize BASE and ZC 120 NON FLAMMABLE CURING AGENT separately for possible sedimentation.
- If necessary, use compressed air to facilitate this separation. Do not use any tools to force the separation of the model from the mold.
- Working time and setting time are reduced if the temperature exceeds 23°C (e.g., if the temperature is 40°C, the working time and setting time are approximately cut in half). If the temperature is less than 23°C, the working time and setting time increase considerably.

#### 5. Physical and Chemical Characteristics

*The figures provided are only intended as a guide and should not be used in preparing specifications.*

##### Component BASE (uncured)

Properties	Specifications	Analytical Method
Viscosity	<40000 cP	Internal Method (Brookfield)
Density (Metric system, 23°C/ 73°F)	1,22 g/cc	

##### Base + Catalyst (cured components)

Properties	Specifications	Analytical Method
Mixing Ratio	100:5	n.a.
Working time/Pot life (23°C/ 73°F) *	50	Internal Method (Brookfield)
Setting time (23°C/ 73°F)	24 h	
Shore A hardness after 24 hours, 23°C	19 shA	ASTM D2240
Shore A hardness after 72 hours, 23°C	21 shA	ASTM D2240
Tensile Strength (Metric System, 23°)	3 N/mm <sup>2</sup>	ASTM D412
Tear strength Die B (Metric System, 23°)	21 N/mm	ASTM D624
Elongation at break (23°)	270%	ASTM D412

\*The working time "WT", also known as "pot life", is the recommended time period for mixing/vacuuming prior to casting. The reported WT shown in the table refers to a standard temperature of 23°C.

Cured Silicone properties are guaranteed within temperatures ranging from a minimum temperature of - 40 °C to a maximum temperature of +200°C.

## 6. Packaging

### ZC 20 BASE

Item code (Internal Zhermack code)	Packaging
DT00171	ZC 20 BASE 1 KG
DT00170	ZC 20 BASE 5KG
DT00172	ZC 20 BASE 20 KG
DT00173	ZC 20 BASE 200 KG

### ZC CURING AGENT

Item code (Internal Zhermack code)	Packaging
DT00678	ZC 120 CURING AGENT NON FLAMMABLE 50 G
DT00677	ZC 120 CURING AGENT NON FLAMMABLE 250 G
DT00676	ZC 120 CURING AGENT NON FLAMMABLE 1KG
DT00679	ZC 120 CURING AGENT NON FLAMMABLE 2X5KG

### THIXO AGENT

Item code (Internal Zhermack code)	Packaging
DT00673	THIXO AGENT SILICONE 250g

## 7. Shelf life and storage conditions

The “Best use before end” date of each batch is shown on the product label.

12 months if stored correctly at a temperature between 5° and 27°C (41° - 80°F).

## 8. Notes

The advice provided as oral or written recommendations or through product use demonstrations are based on the Company knowledge.

Use and application of the product by the user are not subjected to Company’s monitoring or restrictions, therefore the final responsibility falls on the user.

Storage beyond the date specified on the label does not necessary mean that the product is no longer usable. In this case, however, the properties required for the intended use must be checked out for quality assurance reasons. Please contact your Sales Area Manager for support.

## 9. References

n.a.